

# General Purpose Resins

## Materials for High Resolution Models and Rapid Prototyping

**High Detail.** For demanding applications, our carefully-engineered resins capture the finest features in your model.

**Strong and Precise.** Our resins create accurate and robust parts, ideal for rapid prototyping, functional testing and product development.

**Smooth Surface Finish.** Perfectly smooth right out of the printer, parts printed on the Formlabs stereolithography printers have the polish and finish of a final product.



V4 Clear  
FLGPCL04

V4 Grey  
FLGPGR04

V2 Draft  
FLDRGR02

V1 Grey Pro  
FLPRGR01

V4 White  
LGPWH04

V4 Black  
FLGPBL04

V4 Color  
FLGPCB01

\* May not be available in  
all regions

## MATERIAL PROPERTIES DATA

## Standard Resins

The following material properties are comparable for Clear Resin, White Resin, Grey Resin, Black Resin, and Color Kit.

	METRIC <sup>1</sup>		IMPERIAL <sup>1</sup>		METHOD
	Green <sup>2</sup>	Post-Cured <sup>3</sup>	Green <sup>2</sup>	Post-Cured <sup>3</sup>	
<b>Tensile Properties</b>					
Ultimate Tensile Strength	38 MPa	65 MPa	5510 psi	9380 psi	ASTM D638-14
Tensile Modulus	1.6 GPa	2.8 GPa	234 ksi	402 ksi	ASTM D638-14
Elongation at Break	12%	6%	12%	6%	ASTM D638-14
<b>Flexural Properties</b>					
Flexural Modulus	1.3 GPa	2.2 GPa	181 psi	320 psi	ASTM D 790-15
<b>Impact Properties</b>					
Notched Izod	16 J/m	25 J/m	0.3 ft-lbf/in	0.46 ft-lbf/in	ASTM D256-10
<b>Thermal Properties</b>					
Heat Deflection Temp. @ 1.8 MPa	43 °C	58 °C	109 °F	137 °F	ASTM D 648-16
Heat Deflection Temp. @ 0.45 MPa	50 °C	73 °C	121 °F	163 °F	ASTM D 648-16

<sup>1</sup> Material properties can vary with part geometry, print orientation, print settings, and temperature.

<sup>2</sup> Data was obtained from green parts, printed using Form 2, 100 µm, Clear settings, without additional treatments.

<sup>3</sup> Data was obtained from parts printed using Form 2, 100 µm, Clear settings and post-cured with 1.25 mW/cm<sup>2</sup> of 405 nm LED light for 60 minutes at 60 °C.

## SOLVENT COMPATIBILITY

Percent weight gain over 24 hours for a printed and post-cured 1 x 1 x 1 cm cube immersed in respective solvent:

Solvent	24 hr weight gain, %	Solvent	24 hr weight gain, %
Acetic Acid 5%	< 1	Mineral oil (Light)	< 1
Acetone	Sample cracked	Mineral oil (Heavy)	< 1
Bleach ~5% NaOCl	< 1	Salt Water (3.5% NaCl)	< 1
Butyl Acetate	< 1	Skydrol 5	1
Diesel Fuel	< 1	Sodium Hydroxide solution (0.025% PH 10)	< 1
Diethyl glycol Monomethyl Ether	1.7	Strong Acid (HCl conc)	Distorted
Hydraulic Oil	< 1	Water	< 1
Hydrogen peroxide (3%)	< 1	Xylene	< 1
Isooctane (aka gasoline)	< 1		
Isopropyl Alcohol	< 1		