

### **3D Printing Filament**

#### **TECHNICAL DATA SHEET - PRO Series PLA**

Commercial Name: MatterHackers PRO Series PLA

**Designation:** 3D Printing Material

Manufacturer: MatterHackers

Product Description

MatterHackers PRO Series PLA 3D printing filament is a high-quality material made with NatureWorks 4043D Ingeo™, a polylactic acid biopolymer. Made in the USA, PRO Series PLA filament is designed to produce accurate and seamless 3D printed parts perfect for prototyping end-use parts, life-like models, or for taking your everyday 3D printing to a higher caliber.

### **Storage**

PRO Series PLA filament should be stored between 15 - 25°C, in its original packaging, in a clean and dry environment. When following these recommended storage procedures the minimum shelf life will exceed 12 months.

# **Material Specifications**

| PROPERTY                  | VALUE   | TEST METHOD - ISO |
|---------------------------|---------|-------------------|
| Tensile Strength at Break | 53 MPa  | ASTM D882         |
| Tensile Yield Strength    | 60 MPa  | ASTM D882         |
| Tensile Modulus           | 3.6 MPa | ASTM D882         |
| Notched Izod Impact       | 16 J/m  | ASTM D256         |
| Tensile Elongation        | 6%      | ASTM D882         |
| Flexural Strength         | 83 MPa  | ASTM D790         |
| Flexural Modulus          | 3.8 MPa | ASTM D790         |



| Heat Distortion Temperature | 55°C @ 0.45 MPa | ASTM E2092 |
|-----------------------------|-----------------|------------|
| Specific Gravity            | 1.24 g/cc       | ASTM D792  |

# **Filament Specifications**

PROPERTY VALUE

| Diameter 1.75mm             | 1.75 ± 0.05mm           |
|-----------------------------|-------------------------|
| Diameter 2.85mm             | 2.85 ± 0.05mm           |
| Suggested Print Temperature | 190°C - 230°C           |
| Suggested Print Speed       | 50-90+ mm/s             |
| Suggested Bed Temperature   | 60°C - 70°C             |
| Base Resin                  | NatureWorks Ingeo 4043D |

#### **Disclaimer**

The data presented herein is intended for reference purposes only and should not be used as an authoritative source of information for design decisions or quality control purposes. Any final quality or fitness criteria should be based on your own investigations after evaluation and testing. Nothing in this publication is intended to guarantee the specific material properties of any source product or any individual end product. No warranty is made of the merchantability or fitness of any product that may be created with the material described. All specifications and measured results in this document are subject to revision without notice.