Technical Data





SPECS

FEATURES

Photocentric's range of daylight precision firm polymers are ideal for making objects where you want a very hard object with slight compressive ability under high force and minimal shrinkage. Objects will bend a little and stretch slightly when under duress. They exhibit high tensile shear properties and limited elongation, objects can only be bent and compressed with force. Daylight Precision Firm provides excellent imaging in Precision machines. You will experience the benefits of fast exposure times and a wide exposure latitude, allowing you to hold the finest details your precision printer can provide. The solid material is tough, durable and long lasting provided it is stored in dry conditions away from sunlight.

Key benefits include though and durable, highly accurate parts with a good finish and easy to use and finish. Ideal applications are jewellery and models.

PROCESSING INSTRUCTIONS

Follow the procedures laid out in your 3D Liquid Crystal's user manual. Polymer should be poured into the tray away from direct sunlight. Polymer can be reused but should be poured through a filter to remove solid lumps. Keep hood on at all times. Liquid polymer is soluble in water and soap. After making cleaned objects surface tack can be removed by leaving under water in sunlight for 10 minutes.

DATA

Viscosity 560 cPs (At 25°C Brookfield spindle 3)

Hardness 65 Shore D

(Afternation and

(After post exposure)

Tensile strength 26 MPa ASTM D638 (After post exposure)

Tensile strength 10 MPa ASTM D638 (Before post exposure)

Tensile modulus 700 MPa ASTM D638 (After post exposure)

Elongation at break 10%

ASTM D638

Heat deflection temp N/A

ASTM D648

 Storage
 10<t>50°C

 Density
 1.18 g/cm³

AVAILABLE COLOURS

Black

Available in 1kg bottles.

Photocentric Ltd. Cambridge House, Oxney House Peterborough PE1 5YW **UK** email: *info@photocentric.co.uk* Photocentric Inc. 2205 West Parkside Lane, Phoenix, 85027, AZ **USA** email *info@photocentricusa.com*