T > +31 (0)85 060 58 49

E > info@liqcreate.com

l > www.liqcreate.com

## Ligcreate Wax Castable

A wax-based Castable resin for Digital Light Processing (DLP), Liquid Crystal Display (LCD) and laser based 3D-printers. Liquid Castable is perfect for manufacturing jewelry, dental and industrial parts using the direct investment casting method.

### Product description

Liqcreate Wax Castable is a blue wax-based photopolymer with reliable processability and accuracy on LCD/MSLA, DLP and laser based 3D-printers. 3D-printed parts from this material captures intricate features and show crisp details. This wax-based material offers smooth surfaces with clean burnout for a reliable casting process. Create custom made elegant organic geometries according to your preferences with excellent casting for positive and negative engravings. Liqcreate Wax Castable creates perfect casting patterns for jewelry, dental and industrial parts.

#### Key benefits

- High precision
- Wax-based
- Clean & ash free burnout
- Excellent casting of engravings

#### 3D-Printer compatibility

- Phrozen Sonic Mini 4K
- Anycubic Photon
- Elegoo Mars
- All open source 385 420nm DLP, LCD and SLA 3D-printers

#### Order information

Order directly at the <u>Liqcreate store</u> or send your inquiry to <u>order@liqcreate.com</u> with the following order numbers.

Liqcreate Wax Castable 250 gram Order number LWC00250 Liqcreate Wax Castable 1 kg Order number LWC01000



T > +31 (0)85 060 58 49

E > info@liqcreate.com

I > www.liqcreate.com

# **Liqcreate Wax Castable Technical Data**

Liquid properties				
Appearance	Blue liquid	Ec	7.31 mJ/cm <sup>2</sup>	
Viscosity	700 cps at 25°C	D <sub>p</sub> metric	0.29 mm	
Density	1.18 g/cm <sup>2</sup>	D <sub>p</sub> imperial	11.42 mils	

Polymer properties				
Mechanical properties		15 minutes high power LED curing at 60°C		
Description	ASTM Method	Metric	Imperial	
Flexural Strength	D638M	33 MPa	4.8 ksi	
Flexural Modulus	D638M	1.1 GPa	160 ksi	
IZOD Impact (notched)	D256A	n/a	n/a	
Shore D Hardness	D2240	77		
Water sorption	D570-98	0.28 %		
Тд	D7028	n/a	n/a	

These values may vary and depend on individual machine processing and post-curing.

Visit <a href="www.liqcreate.com">www.liqcreate.com</a> for more information about this product and the post processing and burnout schedule.